



**ITC LIMITED – PSPD, UNIT: TRIBENI**  
**SPECIFICATION SHEET**

Doc. No: QP-PM3-034

Ver. No: 5.0 Rev. No: 2.0 Page 1 of 1

Issue Date: 01.11.2020

Grade :

<u>Parameter</u>	<u>Unit</u>	<u>Specification</u>	<u>Test Method</u>
Substance	g/m <sup>2</sup>	30 ± 1.5	T410/ISO536
Thickness	µm	39 ± 3	T411/ISO534
Tensile MD	N/15mm	17 min	T494/ISO1924
Stiffness (MD)	No	10 ± 3	T489/ISO5628
*ISO Opacity %	%	72 min	T519/ISO2471
Brightness ISO	%	84 min	T525/ISO2470
Roughness Top	ml/min	70 ± 20	T535/ISO8791-2
Roughness Wire	ml/min	90 ± 20	T535/ISO8791-2
Water cobb	g/m <sup>2</sup>	25 ± 3	T441/ISO535
Loading	%	13 ± 3	T421
Ash	%	20 ± 3	T211/ISO1762
Wax Pick Top	No	13 min	T459/Dennison test
Wax Pick Wire	No	14 min	T459/Dennison test
Shade	-	Close to standard	ITC Method
Formation	-	Fair	ITC Method

\* Critical Parameter : No deviation allowed on critical parameter

Note :

- 1) All Properties are according to ITC Limited, PSPD Unit : Tribeni Measurements
- 2) Test Climate 23 ± 1°C & 50 ± 2 %RH
- 3) Tolerances are based upon 95% Confidence limits of single mill measurements of conditioned random samples