



**ITC LIMITED – PSPD, UNIT: TRIBENI
SPECIFICATION SHEET**

Doc. No: QP-PM3-148

Ver. No: 5.0 Rev. No: 2.0 Page 1 of 1

Issue Date: 01.11.2020

Grade :

<u>Parameter</u>	<u>Unit</u>	<u>Specification</u>	<u>Test Method</u>
Substance	g/m ²	40 ± 2	T410/ISO536
Thickness	µm	50 ± 3	T411/ISO534
*Tensile MD	N/15mm	45 min	T494/ISO1924
Tensile CD	N/15mm	30 min	T494/ISO1924
KIT Value	No	7 min	ITC Method
Gurley 20 Oz	Sec/100ml	30 min	T460/ISO5636-5
Roughness Top	ml/min	70 ± 20	T535/ISO8791-2
Roughness Wire	ml/min	90 ± 20	T535/ISO8791-2
Water cobb	g/m ²	18 ± 3	T441/ISO535
Formation	-	Fair	ITC Method

* Critical Parameter : No deviation allowed on critical parameter

Note :

- 1) All Properties are according to ITC Limited, PSPD Unit : Tribeni Measurements
- 2) Test Climate 23 ± 1°C & 50 ± 2 %RH
- 3) Tolerances are based upon 95% Confidence limits of single mill measurements of conditioned random samples