



## **AROCRYL - 155** **(PRINT LAMINATION EMULSION)**

**TYPE** : Synthetic Copolymer Emulsion.

### **PHYSICAL CONSTANTS**

**APPEARANCE** : White, free flowing emulsion.

**pH** : 4.50 - 5.50

**FILM** : Clear, transparent on drying.

**VISCOSITY** : 6,000 - 10,000 cps  
Brookfield Viscometer RVT  
Spindle 5, 20 RPM

**USE** : **AROCRYL - 155** is wet-lamination emulsion offering high gloss and high peel strength to emulsion for laminating BOPP / PVC / MET-PET films to printed board/paper surface.  
Note that the lamination emulsion must be coated on the metallized side of the MET-PET film.

**PACKING** : 50 Kg. Plastic Carboy.

**STORAGE** : Store in cool and dry place.  
Keep away from direct sunlight.

**SHELF LIFE** : 6 Months from the date of manufacturing, if stored properly in original packing condition, maintained strictly under recommended storage conditions.

TDS 017 w.e.f.: November 2017

DISCLAIMER: This information contained herein is believed to be accurate & presented in good faith. We do disclaim any liability resulting from the use of the contents of this information Since we cannot control and anticipate the conditions under which this product is used, we do not guarantee that similar results will be obtained by others. Appropriate lab & field trials under intended application and service conditions must be thoroughly evaluated by the user of this product to determine its suitability for a particular application. Any further modification / addition to this product will not be liable for any claim or compensation on M/s Arofine Polymers Pvt Ltd due to any fault arising after the use of the modified product. We reserve the right to alter or change specification without prior notice.

Website: [www.arofines.in](http://www.arofines.in) | Email: [sales@arofines.in](mailto:sales@arofines.in)