



## TECHNICAL DATA SHEET

### GMUND HANF

#### Hanf 100% | 320 g/m<sup>2</sup>

Grammage	ISO 536, g/m <sup>2</sup> :	304 - 336
Caliper	ISO 534, µm:	550 ± 40
Bulk	ISO 534, cm <sup>3</sup> /g:	1,7 ± 0,2
Ash	DIN 54370, %:	> 3
Tensile Index	ISO 1924-2:	
	mean value, length and cross, m:	≥ 2400
	length, m:	≥ 2700
	cross, m:	≥ 2100
Tear Index, Elmendorf method	ISO 1974:	
	mean value, length and cross, mN:	≥ 3000
Dennison-Waxtest	US D2482-66T:	≥ 14
Water Absorption	ISO 535:	
	Cobb 60, g/m <sup>2</sup> :	30 ± 10
pH-Value	DIN 53124:	≥ 7,5