



## PROVISIONAL DATA VALUES – POLYART TC-0236 (PSL IML 70)

TEST	METHOD	UNITS	TARGET
Weight	ISO 536:2012	g/m <sup>2</sup>	70
Thickness	ISO 534:2011	Mils	4.2
		microns	106
Density	ISO 534:2011	g/cm <sup>3</sup>	0.66
Whiteness	TAPPI T 1216 sp-12	%	90
Opacity	ISO 2471:2008	%	92
Roughness (Embossed side) Ra-Rz	ISO 4288:1996	μm	Ra - 1.8 Rz - 11
Surface Resistivity	ASTM D257-14	Ω/□	< 10 <sup>14</sup>
Dyne Level	ASTM 2578-09	dynes/cm	> 42

**Date Created: 5<sup>th</sup> March, 2019**

**Disclaimer:** This data sheet is for a development product and is just a guideline for product typical values. It cannot be used as a specification until the product is commercialized and QA has approved the datasheet.

The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials, or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no endorsement of any product or process, and we expressly disclaim any contrary implication.